



MODENA CENTRO PROVE s.r.l.

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78
Tel. 059 822417 r.a. - Fax 059380281 - e-mail : info@modenacentroprove.it - www.modenacentroprove.com
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

MECCANICA

ECOLOGIA

CERAMICA

ALIMENTARE



Certificato n°
50 100 4582



Diploma
IWR/IT n°
30438



Socio



Membro



Socio

Unione Industriali
Modena



Iscritto

Modena, 25/02/16

To LAPITEC S.p.A.
Via Bassanese, 6 31050 Vedelago
(TV) Italy

Attn. SIG. TONELLATO

MATERIAL and/or SAMPLE to be tested : SINTERED STONES;

Denomination of the Sample : LAPITEC SINTERED STONE ARENA;

Client Reference: Your delivery VS CONSEGNA

date: 13/01/2016

Here attached, you will receive the Test Report of Serial No. **20161042/n**, which shows the results of tests required.

MODENA CENTRO PROVE

MODENA CENTRO PROVE

Director
Sant'Unione dr. Giuseppe



MODENA CENTRO PROVE s.r.l.


Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78
Tel. 059822417 r.a. - Fax 059380281 - e-mail : info@modenacentroprove.it - www.modenacentroprove.com
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364


TEST REPORT: 20161042/1

Modena, 25/02/16

CUSTOMER	LAPITEC S.p.A. Via Bassanese, 6 31050 Vedelago (TV) Italy
MATERIAL and/o SAMPLE to be tested	SINTERED STONES;
Denomination	LAPITEC SINTERED STONE ARENA;
Date of sample reception	13/01/2016;
Kind of test executed	Determination of Slip Resistance
Referring standards	UNI EN 14231:2004
Shifting from standards	None
Equipment	Pendulum cod. MCP C45
Calibration	Rapporto n° 1203244FRI del 30/03/2012
Subcontracted phases	None
Sampling made by	Customer

*The test results showing in this Report are only referred to the sample taken by our staff or supplied by the Customer. He commits himself to reproduce integrally this document. Partial reproduction is forbidden.
The times of retain of the samples was indicated in the offer related to the test report.*

Examiner

P.I. De Pasquale Roberto

MODENA CENTRO PROVE

Ceramic Dept. Responsible
P.I. De Pasquale Roberto

MODENA CENTRO PROVE

Director
Sant'Unione dr. Giuseppe

**MODENA CENTRO PROVE s.r.l.**

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78
Tel. 059822417 r.a. - Fax 059380281 - e-mail : info@modenacentroprove.it - www.modenacentroprove.com
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

DETERMINATION OF SLIP RESISTANCE

Beginning date : 02/19/2016

Analysis ending date : 02/19/2016

SAMPLE : sintered stones marked " LAPITEC SINTERED STONE ARENA "

The test was performed measuring friction resistance between standard rubber surface and the upper side of test specimens.

RESULTS

Wet slipping element and samples used.

Sample N°	Single values(USRV) two directions average
1	68
2	65
3	65
4	65
5	65
6	66
Average	66

REQUIREMENTS

(Norm EN 1341)

Safety surface with USRV values > **35**

 Examiner P.I. De Pasquale Roberto	 MODENA CENTRO PROVE Ceramic Dept. Responsible P.I. De Pasquale Roberto	 MODENA CENTRO PROVE Director Sant'Unione dr. Giuseppe
--	--	---